

**BISSAU – shorts**

|                           |  |   |  |
|---------------------------|--|---|--|
| <p><b>Description</b></p> | <ul style="list-style-type: none"> <li>• elasticated waist,</li> <li>• wide front pockets,</li> <li>• back pocket with velcro,</li> <li>• hammer loop,</li> <li>• rule pocket,</li> <li>• side pocket.</li> </ul> <p><u>Superb colour retention</u><br/>Certified result: 4-5 (range: 1-5)</p>   |                         |  |
| <p><b>Maintenance</b></p> | <p>Maximum wash temperature: 40 °C; Do not bleach ; Tumble drying possible - Drying at lower temperature; Ironing at low temperature (max 110 °C), Do not dry clean.</p> <p>      </p> | <p><b>Item</b></p> <p>V187-0-02 Navy<br/>V187-0-04 Anthracite<br/>V187-0-05 Black<br/>V187-0-08 Green</p> | <p><b>Standards:</b></p> <p>EN ISO 13688:2013</p>  |
|                           |  | <p><b>Sizes</b></p> <p>S - 4XL</p>  |  |

**SAFETY TECHNICAL SPECIFICATIONS**

|                          | Test method   | Description                                    | Cofra result                | Minimum requirement / range |
|--------------------------|---|--|-----------------------------|-----------------------------|
| <b>Background fabric</b> | EN ISO 1833-1977, SECTION 10                              | Composition:                                   | 65% polyester<br>35% cotton |                             |
|                          | EN ISO 12127:1996   | Fabric mass per unit area                      | 245 g/m <sup>2</sup>        |                             |
|                          | EN ISO 13688:2013<br>4.2<br>(ISO 3071)                    | The pH's determination from the watery extract | pH: 7.1                     | 3,5 ≤pH≤ 9,5                |
|                          | EN ISO 13688:2013<br>4.2<br>(EN 14362-1)                  | Search of the aromatic and carcinogenic amines | Not recording               | ≤30 ppm                     |
|                          | EN ISO 13688:2013<br>5.3<br>(ISO 5077)                    | Dimensional change to washing (40°C)           | warp: -1.7%<br>weft: 0.6%   | ±3%                         |
|                          | ISO 105-X12   | Colour fastness to rubbing                     | Dry: 4 - 5<br>Wet: 3 - 4    | 1-5                         |
| EN ISO 105-X11           | Colour fastness to hot pressing (110°C);<br>Colour change | Dry: 4-5<br>Wet: 4-5                           | 1-5                         |                             |

|                |   |                              |          |       |
|----------------|---|------------------------------|----------|-------|
| ISO 105-C06    | Colour fastness to Laundering at 40°C                                   |                              |          | 1-5   |
|                | <i>Colour change</i>  | 4-5                          |          |       |
|                | <i>Staining:</i>  |                              |          |       |
|                | diacetate   | 4-5                          |          |       |
|                | cotton  | 4-5                          |          |       |
|                | nylon   | 4-5                          |          |       |
|                | polyester   | 4-5                          |          |       |
|                | acrylic   | 4-5                          |          |       |
| ISO 105 D01    | Colour fastness to to dry cleaning                                      |                              |          | 1-5   |
|                | <i>Colour change</i>  | 4-5                          |          |       |
|                | <i>Staining:</i>  |                              |          |       |
|                | diacetate   | 4-5                          |          |       |
|                | cotton  | 4-5                          |          |       |
|                | nylon   | 4-5                          |          |       |
|                | polyester   | 4-5                          |          |       |
|                | acrylic   | 4-5                          |          |       |
| ISO 105 E04    | Colour fastness to perspiration   | Acidic                       | Alkaline | 1-5   |
|                | <i>Colour change</i>  | 4-5                          | 4-5      |       |
|                | <i>Staining:</i>  |                              |          |       |
|                | diacetate   | 4-5                          | 4-5      |       |
|                | cotton  | 4-5                          | 4-5      |       |
|                | nylon   | 4-5                          | 4-5      |       |
|                | polyester   | 4-5                          | 4-5      |       |
|                | acrylic   | 4-5                          | 4-5      |       |
| wool           | 4-5   | 4-5                          |          |       |
| EN ISO 13934-1 | Tensile strength  | warp: 1800 N<br>weft: 1000 N |          | 400 N |
| EN ISO 13937-1 | Determination of tear force using ballistic pendulum method (Elmendorf) | warp: 26.9 N<br>weft: 17.5 N |          | ≥12 N |