

Enisej - PADDED JACKET

description

1 breast pocket with zip • mobile phone pocket • 2 wide front pockets • elasticated cuffs • internal pocket • detachable sleeves with zip



maintenance

Maximum temperature: 30°C; Do not bleach; Dry clean with solvents on point F plus Tetrachloroethylene; Do not dry in a tumble dryer; Do not iron



item	V383-0-02 NAVY
standards	EN ISO 13688:2013
sizes	S – 3XL

SAFETY TECHNICAL SPECIFICATIONS

	<i>Test method</i>	<i>description</i>	<i>Cofra result</i>	<i>Minimum requirement / range</i>
Background fabric	EN ISO 1833-1977, SECTION 10	Composition:	65% polyester 35% cotton	
	EN ISO 12127:1996	Weight per unit area	140 g/rsqm	
	ISO 5077-2007, ISO 6330-2000	Dimensional change to washes	Warp: -1,1% Weft: -0,7%	+/- 3%
	EN ISO 13934-1	Tensile strength	Warp: 1300 N Weft: 780 N	Warp: 400 N Weft: 400 N
	EN ISO 13937-2:2000	Tearing strenght	Warp: 25 N Weft: 21 N	Warp: 25 N Weft: 25 N
	EN ISO 105 D01:2010	Colour fastness to dry cleaning	Colour change: 4 – 5 Staining: 4 – 5	01/05/13
	EN ISO 3175-2:2010	Dimensional change to dry washes	Warp: -0,5% Weft: -0,4%	
	ISO 105 B02	Colour Fastness to light	Colour change: 3 – 4	4
	ISO 105-X12:2001	Colour fastness to rubbing	Dry : 3 Wet : 2-3	Dry : 1 - 5 Wet : 1 - 5
	ISO 105-E04:2008	Colour fastness to perspiration	Colour change: 4 – 5 Staining: 4 – 5	Colour change: 4 Staining: 3
	ISO 105-C06	Colour fastness to washes (30°C)	Colour change: 4 – 5 Staining: 4 – 5	Colour change: 3 – 4 Staining: 4 - 5
	ISO-105-X11/94	Colour fastness to hot pressing	Dry: 4-5 Wet: 4-5	1 – 5 1 – 5
	EN340/03 paragraph 4.2 (EN 1413)	The PH's determination from the watery extract	PH : 7,8	3,5<PH≤9,5
	EN340/03 paragraph 4.2 (prEN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm
Lining	EN ISO 1833-1977, SECTION 10	Composition:	100% polyester	
	EN ISO 12127:1996	Weight per unit area	65 gr/sqm	

Padding	Composition:	100% polyester
	EN ISO 12127:1996	Weight per unit area