

Turin – padded jacket							
Description	<ul style="list-style-type: none"> - 2 front pockets with zip; - 2 internal pockets; - front opening with zip; - elasticated cuffs. 						
Maintenance	Maximum wash temperature: 30 °C; Do not bleach; Do not dry clean; Do not dry in a tumble dryer; Do not iron.						
	<table border="1" style="width: 100%;"> <tr> <td style="width: 50%;">Item</td> <td>V355-0-02 (navy/yellow) V355-0-04 (antracite/orange) V355-0-05 (black/lime) V355-0-08 (green/rust)</td> </tr> <tr> <td>Standards:</td> <td>EN ISO 13688:2013</td> </tr> <tr> <td>Sizes</td> <td>S - 3XL</td> </tr> </table>	Item	V355-0-02 (navy/yellow) V355-0-04 (antracite/orange) V355-0-05 (black/lime) V355-0-08 (green/rust)	Standards:	EN ISO 13688:2013	Sizes	S - 3XL
	Item	V355-0-02 (navy/yellow) V355-0-04 (antracite/orange) V355-0-05 (black/lime) V355-0-08 (green/rust)					
Standards:	EN ISO 13688:2013						
Sizes	S - 3XL						

SAFETY TECHNICAL SPECIFICATIONS

	Test method	Description	Cofra result		Minimum requirement / range
Background fabric	EN ISO 1833-1977, SECTION 10	Composition:	100% nylon mini doobby/polyurethane coated		
	EN ISO 12127:1996	Fabric mass per unit area	85 g/mq		
	EN ISO 13688:2013 4.2 (ISO 5077)	Dimensional change to washing after 5 wash (30°C)	warp: -2.9%	weft: -3.0%	±3%
	EN ISO 13688:2013 4.2 (EN 1413)	The PH's determination from the watery extract	pH=4,5		3,5 ≤pH≤ 9,5
	EN ISO 13688:2013 4.2 (EN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording		≤30 ppm
	ISO 105-X12	Colour fastness to rubbing	dry		1 - 5
		Staining:	4-5		
	ISO 105-E04	Colour fastness to perspiration	Acidic	Alkaline	1 - 5
		Colour change	4-5	4-5	
		Staining:			
	diacetate	4-5	4-5		
	cotton	4-5	4-5		
	nylon	4-5	4-5		
	polyester	4-5	4-5		
	acrylic	4-5	4-5		
	wool	4-5	4-5		

	ISO 105-C06	Colour fastness to Laundering at 40°C <i>Colour change</i> <i>Staining:</i> diacetate cotton nylon polyester acrylic wool	4-5 4-5 4-5 4-5 4-5 4-5 4-5	1 - 5
	EN ISO 105-B02	Colour fastness to light (test with xenon arc lamp)	3	1 - 5
	ISO 1421	Tensile strength	warp: 663 N weft: 422 N	
	ISO 4674-1	Tear resistance of coated or laminated fabrics	warp: 27 N weft: 28 N	
	ISO 12947-2	Determination of the abrasion resistance of fabrics by the Martindale method (12Kpa)	>20000 cycles	
	ISO 15496	Measurement of permeability to water vapor of textiles	4562.1 (g/m ² x 24h)	
	EN 20811	Determination of resistance to water penetration. - Wp [Pa] (before each pretreatment)	Wp >13000 Pa	CLASS 1 Wp ≥ 8000 Pa CLASS 2 no test required CLASS 3 no test required
Lining	EN ISO 1833-1977, SECTION 10	Composition:	100% polyester	
Padding	EN ISO 1833-1977, SECTION 10	Composition:	100% polyester	
	EN ISO 12127:1996	Fabric mass per unit area	140 g/mq	