



UCHAMI – jacket							
Description	<ul style="list-style-type: none"> – 1 breast pocket with zip, – 2 wide lower pockets with zip, – front opening with zip, – hood, – reinforced elbows, – fleece inner lining. 						
							
Maintenance	<p>Maximum wash temperature: 30 °C; Do not bleach; Do not dry clean; Do not dry in a tumble dryer; Do not iron.</p> <p>  </p>						
	<table border="1" style="width: 100%;"> <tr> <td style="width: 30%;">Item</td> <td>V376-0-02 navy/black/royal V376-0-04 anthracite/black/lime V376-0-05 black/anthracite/red</td> </tr> <tr> <td>Standards:</td> <td>EN ISO 13688:2013</td> </tr> <tr> <td>Sizes</td> <td>S - 4XL</td> </tr> </table>	Item	V376-0-02 navy/black/royal V376-0-04 anthracite/black/lime V376-0-05 black/anthracite/red	Standards:	EN ISO 13688:2013	Sizes	S - 4XL
Item	V376-0-02 navy/black/royal V376-0-04 anthracite/black/lime V376-0-05 black/anthracite/red						
Standards:	EN ISO 13688:2013						
Sizes	S - 4XL						

SAFETY TECHNICAL SPECIFICATIONS

Test method	Description	Cofra result	Minimum requirement / range
Knitted fabric + Inner fleece	EN ISO 1833-1977, SECTION 10	Composition:	100% polyester
	EN ISO 12127:1996	Fabric mass per unit area	400 g/mq
	EN ISO 13688:2013 5.3 (ISO 5077)	Dimensional change	warp: -1.8% weft: -1.3% ±3%
	EN ISO 13688:2013 4.2 (ISO 3071)	The PH's determination from the watery extract	pH=6,6 3,5 ≤pH≤ 9,5
	EN ISO 13688:2013 4.2 (EN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording ≤30 ppm
	ISO 105-X12	Colour fastness to rubbing <i>Staining:</i>	Dry 4-5 Wet 4-5 1 - 5
	EN ISO 105-B02	Colour fastness to light	5 1 - 5

	ISO 105-C06	Colour fastness to Laundering at 30°C <i>Colour change</i> <i>Staining:</i> diacetate cotton nylon polyester acrylic wool	4-5 4 4-5 4 4-5 4-5 4-5	1 - 5
	ISO 105-E04	Colour fastness to perspiration <i>Colour change</i> <i>Staining:</i> diacetate cotton nylon polyester acrylic wool	Acidic 4-5 4-5 4-5 4-5 4-5 4-5 4-5 Alkaline 4-5 4-5 4-5 4-5 4-5	1 - 5
	EN ISO 12945-2	Determination of fabric propensity to surface fuzzing and to pilling	after 2000 cycles 4	1-5
Softshell fabric	EN ISO 1833-1977, SECTION 10	Composition:	100% polyester + wind-protecting membrane, 300 g/m ² - INTERNAL: 100% polyester	
	EN ISO 12127:1996	Fabric mass per unit area	300 g/mq	
	EN ISO 13688:2013 4.2 (EN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm
	EN ISO 13688:2013 4.2 (ISO 3071)	The PH's determination from the watery extract	pH=6,7	3,5 ≤pH≤ 9,5
	EN ISO 13688:2013 5.3 (ISO 5077)	Dimensional change	warp: -0.6% weft: 0%	±3%
	ISO 105-C06	Colour fastness to Laundering at 30°C <i>Colour change</i> <i>Staining:</i> diacetate cotton nylon polyester acrylic wool	4-5 4-5 4 4 4-5 4-5 4-5	1 - 5

ISO 105-E04	Colour fastness to perspiration <i>Colour change</i> <i>Staining:</i> diacetate cotton nylon polyester acrylic wool	Acidic 4-5 4 4 4 4-5 4-5	Alkaline 4-5 4 3-4 4 4 4	1 - 5
EN 20811	Determination of resistance to water penetration.	Wp >13000 Pa		<i>classe 1 : no test required</i> <i>classe 2 : Wp >= 8.000 Pa</i> <i>classe 3 : Wp >= 13.000 Pa</i>
EN 31092	Water vapour resistance R _{et} [m ² Pa/W]	R _{et} = 67.9 [m ² Pa/W]		
ISO 15496	Measurement of permeability to water vapor of textiles	3404.5 (g/m ² x 24h)		